THE INVENTION CLAIMED IS

10

1. In a solid oxide fuel cell operating at a temperature in the range of 400-700°C, the improvement comprising;

an anode including doped-ceria, and a cathode including cobalt iron

based materials.

- 2. The improvement of Claim 1, wherein said anode is composed of NiO/doped-ceria.
- 3. The improvement of Claim 1, wherein said doped-ceria includes doping elements selected from the group consisting of samarium oxide, gadolinium oxide, yttria oxide, and lanthanide oxide.
- 4. The improvement of Claim 1, wherein said fuel cell includes a pore former to create pores therein.
- 5. The improvement of Claim 4, wherein said pore formed is selected from the group consisting of starch and carbon.
- 6. The improvement of Claim 1, wherein said electrolyte comprises material selected from the group consisting of doped-ceria, doped-zirconia with a thin layer of doped-ceria, and doped-ceria/doped-zirconia.
- 7. The improvement of Claim 1, wherein said electrode is selected from the group consisting of (La, Sr)(Co Fe)O₃, and (La,Ca)(Co, Fe, Mn)O₃.
- 8. The improvement of Claim 1, wherein said doped-ceria in said electrolyte comprises colloidal spray deposited doped-ceria, or aerosol spray casting.
- 9. The improvement of Claim 1, wherein said cobalt iron based material is deposited by colloidal spray deposition or aerosol spray casting.

10. In a method for fabricating ceria-based solid oxide fuel cells, the improvement including forming the ceria-based material by colloidal spray deposition.

The improvement of Claim 1, additionally including forming an electrode of the fuel cells from a cobalt, iron, manganese based material-by-colloidal-spray deposition.

- 12. A ceria-based solid oxide fuel cell including:

 an anode containing doped-ceria,

 an electrolyte containing doped-ceria,

 an electrode containing cobalt iron based materials, and

 a fuel selected from the group consisting of hydrogen, methane, methanol,

 propane, butane and other hydrocarbons
- 13. The fuel cell of Claim 12, operating in a temperature range of 400-700°C.
- 14. The fuel cell of Claim 12, wherein said fuel is composed of hydrogen or methane, and wherein the operating temperature is about 550°C.
- The fuel cell of Claim 12, wherein said fuel is hydrogen, and wherein a power output of up to 400mW/cm^2 is produced at an operating temperature of $550 ^{\circ}\text{C}$.
- 16. The fuel cell of Claim 12, wherein said fuel is methane, and wherein a power output of 320mW/cm² is produced at an operating temperature of 550°C.
- 17. The fuel cell of Claim 12, wherein said anode comprises NiO/doped-ceria.
- 18. The fuel cell of Claim 17, wherein said electrolyte additionally includes doped-zirconia.
- 19. The fuel cell of Claim 18, wherein said electrode comprises (La, Sr)(Co, Fe, Mn) O₃.
- 20. The fuel cell of Claim 19, wherein said doped-ceria is doped with samarium oxide, yttria oxide, lanthamide oxide, or gadolinium oxide.